

ELECTRODE WIRE FOR WIRE ELECTRICAL DISCHARGE MACHINING

Patent number: JP2003291030
Publication date: 2003-10-14
Inventor: IZUI ISAO; HASEGAWA SHIGEMI; YOSHIMOTO
MASAKAZU; KIMOTO YOICHIRO
Applicant: OKI ELECTRIC CABLE
Classification:
- international: **B23H7/08; C22C9/04; B23H7/08; C22C9/04; (IPC1-7):**
B23H7/08; C22C9/04
- european:
Application number: JP20020095316 20020329
Priority number(s): JP20020095316 20020329

Report a data error here

Abstract of JP2003291030

PROBLEM TO BE SOLVED: To provide a structure of electrode wire for wire electrical discharge machining for manufacturing wire with reduced manufacturing processes and greatly improved machining speed as compared with conventional electrode wire and providing roughness of a finished surface and dimension accuracy equivalent to those by conventional electrode wire, and a method for manufacturing the same.

SOLUTION: Electrode wire for electrical discharge machining 1 has a core material 2 composed of brass containing 68-82 wt.% of Cu and rest of Zn and a copper-zinc alloy multi layer structure having concentration gradient with increasing zinc concentration as it gets apart from the core material 2. An outermost layer contains 95% or more zinc concentration and has a thickness of 8-16% of total outer diameter. The method for manufacturing the electrode wire for electrical discharge machining 1 comprises a first process to apply zinc plating of a thickness of 10-50 [μ m] on brass wire of 0.5-1.3 mm containing 68-82% wt.% of Cu and rest of Zn, a second process to perform heat treatment by passing through a heating furnace of 500-2,000 mm length generating 800-900[deg.]C oxidation atmosphere at 3.0-10 m/min speed, and a third process to extend the wire thereafter.

COPYRIGHT: (C)2004,JPO

Data supplied from the **esp@cenet** database - Worldwide